

RAVE REVIEWS

No wonder Resisthane™ *Plus* was rated best all around water-based finish for the buck by Fine Woodworking magazine in December of 2006. This *internally cross-linked* water-based lacquer is extremely tough and durable with clarity, depth and richness like no other water-based finish on the market. Above all, it provides outstanding warmth and grain definition like no other water-based wood lacquer on the market.

ENVIRONMENTALLY RESPONSIBLE

This **Green Technology** finish is very low in VOC, making it very environmentally friendly and safe even for chemically sensitive individuals, during and after application. Makes finishing wood safe and easy. No window of recoatability; recoat any time. No need to sand between coats, if so desired. 100% burn-in within 48 hours. Self-sealing (recommended) or apply over our Clear Wood Sealer if so desired.

USE AND APPLICATION

For finishing and refinishing of all interior furniture, kitchen cabinets, table tops, office furniture, antiques, and paneling. Not recommended for bar tops, restaurant tables, conference tables, or flooring - use our **POLYSHIELD®** instead, or the **Green Technology™ GYMCOTE™** for flooring application. Meets KCMA standards for kitchen cabinets.

Apply by spray or a good quality foam brush. Excellent flow and leveling properties. For best results, please follow label directions prior to use.



SPECIFICATIONS

| | |
|-----------------------------------|-------------------------|
| Solids: ----- | 35% |
| Viscosity, # 4 Ford Cup:----- | 30 sec |
| Coverage:----- | 400 sq ft per gal |
| Recoat Time @ 75°F, 45% RH: ----- | 1 hour |
| Drying Time @ 75°F, 45% RH ----- | Dust free 10-20 minutes |
| VOC ----- | 0.5 lbs/gal, 60 g/L |

For thinning requirements, thin only with water - up to 10% by volume.

Do not use or apply at temperatures (ambient and/or object surfaces) below 50°F. Film clarity, cure and hardness will be affected.

HYDROCOTE® COMPANY, INC.

800-229-4937

New Brunswick, NJ 08901

Fax: 732-828-7325

For More Information visit www.hydrocote.com